





Outline

- Review of proposed changes to heights and areas requirements
- NRC/CWC/FPInnovations midrise wood construction research project
- Component Additive Method proposals and other activities

Canadian Conseil
Wood canadier
Council du bois

Division B – Subsection 3.2.2

Building Size and Construction Relative to Occupancy

- 3.2.2.20 to 3.2.2.83
- Combustible Construction, Heavy Timber Construction and Noncombustible Construction

Canadian Conseil Wood canadier Council du bois

2010 NBCC Wood Construction

Occupancy Type	No. of storeys	Max. Allowable Building Area ¹ (m ²) (unsprinklered)	Max. Allowable Building Area (m²) (sprinklered)		
Residential	1	2400	7 200		
(Group C)	2	1200	3 600		
	3	800	2 400		
	4	-	1800		

 Facing one street, for buildings with 1hr. FRR. (Increases by 25% if facing two streets and 50% if facing 3 streets.)

Code references:

Unsprinklered - 3.2.2.51

Sprinklered - 3.2.2.50.

Canadian Conseil Wood canadien Council du bois

2010 NBCC Wood Construction


Occupancy Type	No. of storeys	Max. Allowable Building Area ¹ (m ²) (unsprinklered)	Max. Allowable Building Area (m²) (sprinklered)		
Business and	1	7 200	14 400		
personal	2	3 600	7 200		
services (Group D)	3	2 400	4 800		
(Group D)	4	-	3 600		


1. Facing three streets, 45-minute FRR

Code references:


Unsprinklered - 3.2.2.58.

Sprinklered - 3.2.2.57. & 3.2.2.59.












National Code Change Proposals


- www.nationalcodes.nrc.gc.ca
- October 15 December 23, 2013
- Much more than just 5- and 6-storey combustible construction


Canadian Conseil


























Sprinklers

For 5- and 6-storey Group C:

 NFPA 13 required, as well as additional sprinklering of exterior balconies and decks

(balconies or decks exceeding 610 mm)



Exterior Walls

Cladding:

- · noncombustible cladding, or
- cladding which passes the requirements when tested in accordance with CAN/ULC-S134 "Standard Method of Fire Test of Exterior Wall <u>Assemblies</u>"
- 10% permitted to combustible cladding

Firefighting Access

 Require 25% of the perimeter to be within 15 m of a street or access route






Firefighting Access

 Street or access route to have elevation not more than 2 m below the floor of the first storey





Additional Fire Protection Features

- More fire blocking in all (including sprinklered) combustible concealed spaces (unless filled with noncombustible insulation with max. 50 mm gap)
- Double duration of emergency power supply for lighting and fire alarm systems (1 hr.)



Construction and Demolition Sites (National Fire Code)

- Fencing, boarding or barricades
- Access control when site unattended
- Required water supply available when combustible material arrives on site
- Unobstructed clearance around hydrants



Construction and Demolition Sites (National Fire Code)

- Minimum clearance (3 m) maintained between exits and waste containers
- Smoking area requirements
- Minimum clearances between roofing kettles and exits, means of egress and exposed combustible materials
- Site identification
- · Construction access stairway



Additional Changes

Earthquake design

- Reduce risk of sway-storey seismic behaviour, which could lead to building collapse
- Improved safety factor for lateral earthquake force



3 NAC-CNAC

Building Envelope

- Additional guidance for design to reduce risk of:
 - inadequate design features for increased wind loading for higher buildings
 - potential detrimental effects of moisture for higher building





Wood Building Research

- National Research Council of Canada
- Canadian Wood Council
- FPInnovations
- Province of British Columbia
- Province of Ontario
- Province of Quebec



Wood Building Research

- Building Envelope: Control of Heat, Air, Moisture and Precipitation (HAMP)
- Acoustics: STC Ratings, Sound Flanking
- Fire: Encapsulation, Fire Resistance and Exterior Walls



Building Envelope: HAMP


- Identify envelope details, climate locations and loads;
- Water penetration lab experiments
- Hygrothermal modeling and analysis




Building Envelope: HAMP


- Assess whether alternate woodbased building envelope solutions developed
 - Meet NBC 2010 Part 5 requirements
 - Meet NECB 2011 maximum envelope overall heat transmission requirements































Midrise Research CAN/ULC-S134

	Sheathing	Wall Construction	Insulation		
1	12.7 mm Gypsum	Untreated wood 2 x 6, 400 mm o.c.	Spray Polyurethane Foam		
2	Sheathing	Simulated CLT + 2 x 6, 600 mm o.c. furring	XPS Foam Insulation		
3	15.9 mm FRTW Plywood	Simulated CLT + 2 x 6, 600 mm o.c. furring	XPS Foam Insulation		
4		Untreated wood 2 x 6, 400 mm o.c.	Spray Polyurethane Foam		

Canadian Conseil Wood canadie Council du bois

Fire: Encapsulation

- · Intermediate-scale fire testing
 - horizontal furnace





- Large-scale fire testing -
 - Light-frame wood
 - Cross-laminated timber
 - Light-frame steel

Canadian Conseil
Wood canadien
Council du bois







Fire: Encapsulation • Large-scale fire testing:

Fire Resistance Ratings Wood-frame Construction

Component Additive Method (CAM)

- NBCC 2010, Division B, Appendix D-2.3 for Framed Walls, Floors and Roofs
- Last revised for 1995 NBCC
- National Codes Public Consultation proposals

Fire Resistance Ratings Wood-frame Construction

CAM values proposed for:

- Double layers of gypsum board (walls and floors)
- Wood I-joists, more wood truss types
- Additional insulation types/locations and floor toppings
- Use of resilient metal channels

Canadian Conseil Wood canadien Council du bois

2010 Component **Additive Method (CAM)**

Wood Wall Assemblies

Membrane Members		ers	Insulation				
Description	Assigned time (min)	Description	Assigned time (min)	Description	Assigned time (min)	Total FRR* [‡]	
				MFI (Loadbearing & Nonloadbearing)	15	60	
		Wood Studs @ 400 mm o.c. Wood Studs @ 600 mm o.c.	20	GFI (Nonloadbearing Only)	5	50	
12.7 mm Type X	0.5			None (Loadbearing & Nonloadbearing) & GFI (Loadbearing)	0	45	
Gypsum Board	25			MFI (Loadbearing & Nonloadbearing)	15	55	
			15	GFI (Nonloadbearing Only)	5	45	
				None (Loadbearing & Nonloadbearing) & GFI (Loadbearing)	0	40	
		\\\ Ot -	100 mm 20	MFI (Loadbearing & Nonloadbearing)	15	75	
	40	Wood Studs @ 400 mm o.c.		GFI (Nonloadbearing Only)	5	65	
15.9 mm Type X				None (Loadbearing & Nonloadbearing) & GFI (Loadbearing)	0	60	
Gypsum Board	40	Wood Studs	15	MFI (Loadbearing & Nonloadbearing)	15	70	
				GFI (Nonloadbearing Only)	5	60	
		@ 600 mm o.c.		None (Loadbearing & Nonloadbearing) & GFI (Loadbearing)	0	55	

- * for this to be applicable:
- must meet minimum fastener penetration requirements all edges of GB must be supported, except for 15.9 mm Type X installed horizontally where horizontal joints can be unsupported if framing @ 400 mm o.c. maximum
- [‡] applicable to exterior wall assemblies requiring FRR from inside that have GB on interior and exterior sheathing + cladding with mineral fibre insulation with area density of ≥1.22 kg/m² Con

2015 Component **Additive Method (CAM)**

Wood Wall Assemblies

Membrane		Members		Insulation	Total		
Description	Assigned time (min)	Description	Assigned time (min)	Description	Assigned time (min)	FRR*	
	50	Wood Studs @ 400 mm o.c.	20	RFI	15	85	
Loadbearing				CFI – dry-blown	10	80	
2 layers of				None & GFI	0	70	
12.7 mm Type X		Wood Studs @ 600 mm o.c.	15	RFI	15	80	
Gypsum Board				CFI – dry-blown	10	75	
				None & GFI	0	65	
	rs of Type X	Wood Studs @ 400 mm o.c.	20	RFI	15	115	
Non-loadbearing				GFI	5	105	
2 layers of 12.7 mm Type X Gypsum Board				None	0	100	
		Wood Studs @	15	RFI	15	110	
				GFI	5	100	
		600 mm o.c.		None	0	95	

- * for this to be applicable:
- nust meet minimum fastener penetration requirements all edges of GB must be supported, except for 15.9 mm Type X installed horizontally where horizontal joints can be unsupported if framing @ 400 mm o.c. maximum

Also, resilient metal channels are permitted to be installed at max. spacing of 400 mm o.c. with no effect on the rating of the wall assembly.



2010 Component **Additive Method (CAM)**

Wood Floor Assemblies

Membrane		Members		
Description	Assigned time (min)	Description	Assigned time (min)	Total FRR*
1 layer of 12.7 mm	25	Wood Joists @ 400 mm o.c. maximum	10	35
Type X Gypsum Board		Wood Trusses @ 600 mm o.c. maximum	5	30
1 layer of 15.9 mm		Wood Joists @ 400 mm o.c. maximum	10	50
Type X Gypsum Board	40	Wood Trusses @ 600 mm o.c. maximum	5	45

* for this to be applicable:

- must have also minimum subfloor + flooring combination
- all edges of GB must be supported
- must meet minimum fastener penetration requirements; mineral fibre insulation of rock or slag does not affect FRR in wood floors as long as held in by resilient channels or furring channels

2015 Component **Additive Method (CAM)**

Wood Floor Assemblies


Membrane		Members		Insulation		Topping			
Description	Resilient Metal Channels	Assigned time (min)	Description	Assigned time (min)	Description	Assigned time (min)	Description	Assigned time (min)	Total FRR*
2 layers of 12.7 mm	Spaced ≤ 400 mm o.c.		Wood Joists, Trusses,		RFI or CFI (wet-	5	None or Gypsum- concrete	0	65
Type X	(or direct	50		10	sprayed)		Concrete	5	70
Gypsum Board	applied to members ≤		mm o.c.	nm o c	None or GFI	0	None or Gypsum- concrete	0	60
Board	400 mm o.c.)		IIIaxiiiiuiii				Concrete	5	65
2 layers of	12.7 mm Type X Gypsum Spaced \$ 600 mm o.c. (or direct applied)		Wood Joists,		RFI or CFI (wet-	5	None or Gypsum- concrete	0	60
		4.5	Trusses, I-joists @ 600 mm o.c. maximum	10	sprayed)		Concrete	5	65
						None or GFI	0	None or Gypsum- concrete	0
Board				maximum	maximum	IIIdAIIIIdiii		Concrete	5
2 layer of	Spaced ≤ 600		Wood Joists, Trusses,		RFI or CFI (wet-	5	None or Gypsum- concrete	0	75
	15.9 mm Spaced 3 000 mm o.c.	am a a ll iointa @ 60	I-joists @ 600	@ enn	sprayed)		Concrete	5	80
Gypsum (or direct	(or direct 60 mm o.c.	10	None or GFI	0	None or Gypsum- concrete	0	70		
Board	,					_	Concrete	5	75

- * for this to be applicable:
- must have minimum subfloor all edges of GB must be supported must meet minimum fastener penetration requirements

Fire Resistance Ratings Massive Timber

CSA 086 - 2014 edition

- Annex B:
 "Fire resistance of large cross-section wood elements"
- Informative



Additional Activities

- Fire Protection Research Foundation (NFPA) Fire Safety Challenges of Tall Wood Buildings Report (November 2013)
- CWC Heights & Areas Historic Fact-finding Report (2014)
- FPInnovations Tall Wood Building Guide (Spring 2014)
- 2nd Ed. of FPInnovations CLT Handbook Fire Chapter (Spring 2014)
- NSERC NEWBuildS PROJECT T3-3-C7: FIRE BEHAVIOUR OF CROSS LAMINATED TIMBER PANELS





